

SpECcoat Zn25

ONE PART ZINC EPOXY PRIMER

DESCRIPTION

SpECcoat Zn25 is a one-part primer based on a blend of epoxy resin and zinc.

TYPICAL USES

SpECcoat Zn25 is recommended as a primer for exposed reinforcement where a corrosion resistant primer is specified. It is specifically developed for use with **SpECbuild** cementitious repair mortars.

ADVANTAGES

- One part
- High metallic zinc content inhibits corrosion
- Compatible with **SpECbuild** cementitious mortars

TECHNICAL DATA

Specific Gravity	1.925			
Overcoating time:				
@	10°C	20°C	30°C	40°C
(max)	120min	60min	40min	20min
(min)	60min	30min	20min	10min
Typical wft	150 microns			
Typical dft	45 microns			

APPLICATION INSTRUCTIONS

Preparation

It is essential that adequate preparation is carried out prior to the application of **SpECcoat Zn25**. If it is determined that chloride ingress was the cause of the corrosion, the grit blasted area should be treated by high pressure washing.

Any corroded reinforcing steel should be grit blasted to bright metal, to remove all scale and corrosion products. It is essential this treatment continues over the rear of the reinforcing steel.

Application

It is essential that there is no delay in the application of **SpECcoat Zn25** once the steel

is dry. Delays greater than one hour should be avoided.

Stir the contents of the tin to ensure that any settlement is redispersed.

The product should be applied by brush ensuring continuous coverage over the total surface area of the exposed steel. It may be necessary to apply a second coat if it is felt that some gaps may exist in the first coat. In this case allow the first coat to dry fully before application of the second coat. (Refer to Technical Data).

Once the priming operation is complete and has fully dried, it is essential that the repair mortar is applied as soon as possible. In environments where high temperature & high humidity prevail, this period should not exceed three days.

PACKAGING & YIELD

1 litre, 2.5 litre and 5 litre tins.

COVERAGE

Typically 7.0 m²/litre.

EQUIPMENT CLEANING

Use **SpECcoat Cleaning Fluid** immediately after use.

STORAGE AND SHELF LIFE

SpECcoat Zn25 has a shelf life of 6 months when stored in a dry cool store in unopened packaging.

HEALTH AND SAFETY

SpECcoat Zn25 & SpECcoat Cleaning Fluid should not be permitted to contact skin and eyes. It is essential that adequate ventilation is provided and that all personnel should avoid inhaling the vapours produced. If working is necessary in confined areas, it is strongly recommended that sealed respiratory equipment is utilised.

Eye contact Rinse with copious amounts of clean water and seek medical attention.

Skin contact Rinse with copious amounts of clean water followed by thorough cleaning with soap and water.

Do NOT USE SOLVENTS

Ingestion Seek immediate medical attention.

DO NOT INDUCE VOMITING

FLAMMABILITY

SpECcoat Zn25 and SpECcoat Cleaning Fluid are flammable. Do not expose to naked flames or other ignition sources.

FLASHPOINT

SpECcoat Zn25 >40 °C

SpECcoat Cleaning Fluid >40 °C

Issue 7: 05/2011

QA-054

Whilst the information and/or specifications given are, to the best of our knowledge, true and accurate, no warranty is given or implied in connection with any recommendations or suggestions made by us, our representatives, agents or distributors as the conditions of use and labour involved are beyond our control.

If it is proven that the product does not perform as described in our TDS, SpEC's liability extends solely to the free replacement of product, once the claim has been accepted after due investigation by SpEC. SpEC will not entertain any claims involving any form of consequential costs or damages such as shipping costs, custom duties, damages to third parties, damages to structures, penalties from delay of a project or any other form of consequential damage.

SPECIALITY ENGINEERING CHEMICALS

PO Box 61347, Dubai, United Arab Emirates. Telephone: +971 4 883 6662, Fax: +971 4 883 7696
E-mail: info@spec.ae; Skype ID: [spec.sales](https://www.skype.com/en/contacts/voice/spec.sales)

www.spec.ae